



Granol'therm DP (EPS)

Meetstaat

Granol'therm DP (EPS) – Isolatiewaarde uit geëxpandeerd polystyreen (EPS).

#P1 Isolatiewaarde geëxpandeerd polystyreen, λ 0,038 W/(m.K) [type Granol'therm DP 100]	FH [m ²]
#P2 Isolatiewaarde geëxpandeerd polystyreen, λ 0,035 W/(m.K) [type Granol'therm DP 105]	FH [m ²]
#P3 Isolatiewaarde geëxpandeerd polystyreen, λ 0,034 W/(m.K) [type Granol'therm DP 134]	FH [m ²]
#P4 Isolatiewaarde geëxpandeerd polystyreen, λ 0,032 W/(m.K) [type Granol'therm DP 160]	FH [m ²]